

ASODUR®-SG2



SCHOMBURG

SCHOMBURG GmbH & Co. KG, with its two divisions, is an international firm supplying the construction sector with high quality, innovative building materials. With a state of the art production facility, internal R&D team and excellent technical expertise SCHOMBURG is a dominant market force.

SCHOMBURG GmbH Detmold reaches the German market through a network of distributors specializing in materials for:

- Waterproofing and restoration
- Tile and natural stone setting systems
- Screeds and floor coatings
- Products for gardening and landscaping construction and other construction materials

SCHOMBURG is a partner for specialised distributors in both the national and international market.

The INDUTECH RETHMEIER GmbH aims its focuses at two branches:

The core competency of the RETHMEIER sales division lies in the concrete construction industry. With a focus on concrete block, pre-cast concrete and ready-mix concrete, they deliver a range of products encompassing:

- Concrete additives
- Form release agents and accessory products
- Concrete Pigments

The INDUTECH sales division services and consults Architects, Engineers and Contractors about products and systems for:

- Industrial flooring
- Parking garage construction
- Roadway and track construction
- Water tank construction, and
- Concrete restoration

Industry professionals value the level of service provided by the SCHOMBURG Group, along with our large range of high quality products.


In order to stay at the forefront of a continuously advancing market we are always investing in research and development of new and current products. This guarantees high quality products, which in turn leads to customer satisfaction.




SCHOMBURG GmbH & Co. KG
Aquafinstraße 2-8
D-32760 Detmold - Germany
phone +49-5231-953-00
fax +49-5231-953-108
mail export@schomburg.de
web www.schomburg.de/en



AQUAFIN International GmbH as holding company of the distribution and also production companies in:
Brazil, Bulgaria, Croatia, Czech Republic, Egypt, Estonia, France, Guinea, Hungary, Iceland, India, Kaliningrad, Kazakhstan, Latvia, Lithuania, Luxembourg, Nepal, Netherlands, Norway, Pakistan, Poland, Qatar, Romania, Russia, Serbia, Slovakia, Switzerland, Tunisia, Turkey, Ukraine, United Arab Emirates, United Kingdom, United States, White Russia





ASODUR®-SG2

combines an unusually wide variety of advantages in one unique product:

- Vapour barrier
- Moisture tolerant
- High chemical resistance
- Excellent adhesion on damp substrates
- Good adhesion after freeze/thaw cycling
- Easy to apply – one coat application
- Functions as negative side waterproofing
- Provides good bonding for additional top coatings such as adhesives, epoxies and self levelers

Areas of application:

Concrete slabs on or below grade such as

- Industrial/retail facilities
- Office buildings
- Hospitals and schools
- Residential slabs

Typical applications:

- Concrete slabs with missing or damaged vapour barriers
- Oil contaminated concrete substrates
- One week old concrete slabs and underlayments
- New concrete slabs with excessive moisture content to receive a flooring or coating



ASODUR®-SG2

ASODUR®-SG2

is a unique 2-component, moisture tolerant, extremely high-density epoxy based product, which prevents the passage of water vapour and moisture through slabs on or below grade, thus eliminating delamination of adhesives, floor coverings and coatings. It also prevents capillary infiltration of oil or other chemicals from the ground and can be used to treat oil-contaminated slabs.

ASODUR®-SG2

reduces water vapour emission levels of up to 25 lbs/1000 ft²·24 hrs (5 g/m²·hrs) to well below accepted levels for subsequent application of flooring systems such as epoxies, vinyl tiles, sheet vinyl, carpets, wood flooring, etc.

Water Vapour Emission Test: Use "Anhydrous Calcium Chloride" testing as per ASTM F 1869-98 to determine the existing water vapour emission rate prior to application of **ASODUR®-SG2**.

Surface Preparation:

Use steel shot blasting, high-pressure water or abrasive (sand) blasting, scarifying or other suitable means to obtain a uniform, absorptive surface, free of existing coatings or any bond inhibitors. (ICRI CSP 2-3 profile.) Rinse all surfaces to be treated with clean water, leaving no standing water.



Failed epoxy flooring due to excessive water vapour transmission.



Surface preparation



Cleaning / rinsing surface from debris.



Mixing AQUAFIN ASODUR®-SG2 in supplied container.



Application step 1, spreading material evenly over surface with squeegee or roller.



Application step 2, scrubbing material into the substrate pores with a brush.



Application step 3, sanding of surface for bonding of subsequent epoxy top-coating.



Finished surface, ready to receive top-coating.

Mixing and Application:

Thoroughly mix resin and hardener (component A & B) as per data sheet instructions.

Pour and spread product in one coat at a rate of 115 ft²/gal (2.8 m²/liter) by roller or squeegee to the moist substrate, and carefully scrub it into the pores with a long handled brush. Follow with a roller to achieve a uniform coverage. Protect treated area from strong sunlight and wind. Indoors, prevent noticeable drafts.

Broadcast #20 mesh (0.5-1.0 mm) sand into fresh application.

Installation time: 1 day

Refer to Technical Data sheet for full application instructions.

ASODUR®-SG2

Adhesion to

New concrete 110 psi
5 days old (0.8 Mpa)

Concrete, moist 550 psi
28 days old (3.8 Mpa)

Concrete, dry 580 psi
28 days old (4.0 Mpa)

Mixing ratio: 100:12 by weight
Density: 15.49 lbs/gal (1.86 kg/l)
Working time: 1 hrs*)
Open to foot traffic: 12 hrs*)
Recoat time: 12 hrs*)
Full strength: 7 days*)
(*) at an ambient temperature of 73 F (23°C) at 60% relative air humidity

Moisture Vapour Transmission:

3 lbs/1000 ft²·24 hrs
(0.6 g/m²·hrs) or less

Permeance:

Refer to product and material safety data sheets for full details.